

SPECIFICATIONS

G220K2M45X37 GRIP SHEET NON-SLIP SHEET

Date: 2009-12-03

| GENERAL DESCRIPTION | | | |
|---------------------|--|--|--|
| Base Material | Recycled paper of a basic weight of 220g per square meter | | |
| Non Slip Coating | Fully Coated on both sides (Alternating Bands and one-side also available) | | |

| TECHNICAL CHARACTERISTICS **See Important Note | | | | | | | |
|--|-----------|------------------------|------|--------|----------------|--|--|
| TEST | UNITS | STANDARD | NOTE | TARGET | SPECIFICATIONS | | |
| Finish Product Weight | g/m² | NF EN ISO 536, 1996 | | 241 | 232 - 249 | | |
| Thickness | μm | NF EN ISO 534, 2005 | | 418 | 398 - 438 | | |
| Resistance to Break under Traction | | NF EN ISO 1924.2, 1995 | | | | | |
| Resistance | kN/m | | MD | 10.3 | ≥ 8.27 | | |
| Resistance | | | CD | 4.4 | ≥ 3.88 | | |
| Length at Break | meter | | MD | 4346 | ≥ 3500 | | |
| Length at Break | meter | | CD | 1869 | ≥ 1640 | | |
| Elongation | % | | MD | 1.6 | ≥ 0.8 | | |
| Elongation | | | CD | 2.4 | ≥ 1.5 | | |
| Bursting Strength | kPa | NF EN ISO 2758, 2004 | | 388 | ≥ 297 | | |
| Coefficient of Static Friction (recto against verso - Angle) | in degree | NF Q 03-083, 1993 | MD | 53.0 | ≥ 46.9 | | |

^{**} **Important Note**: At the time this specification was produced, the technical characteristics were only available for the fully coated version. Data supplied by Endupack SA.

| PACKAGING | | | | | |
|---------------------|---|--|--|--|--|
| Standard Sheet Size | 1140 mm X 940 mm +/- 5 mm (45" X 37" +/- 0.25") | | | | |
| Pallet Size | 1200 mm X 1000 mm (+/- 48" X 40") | | | | |
| Quantity per pallet | 2000 sheets | | | | |
| Unit Load Height | Up to 44" approximately | | | | |
| Unit Load Weight | 1180 lbs (535 kg) approximately | | | | |
| Stocking conditions | Non sensitive to heat or cold. Double stacking is acceptable. | | | | |